

ZGDBSLV PA6GZH (0)

产品定义: PA6+FR

产品特点: 阻燃尼龙 6, 具有良好的柔韧性和热稳定性, 表面光洁度优异, 良好的熔体强度适用于注塑、挤出或吹塑成型。

产品应用: 波纹管、电子电气配件等

ZGDBSLV PA6GZH (0) is a flame retardant PA6 with black color, it provides excellent flexibility and thermal-stability , prominent surface finish, it is applicable to injection & extrusion & blow molding due to its good melt strength.

Product applications: bellows, electrical & electric accessory, etc

典型成型条件**typical molding process**

干燥 dry	鼓风烘箱(drum wind oven): 100-120°C, 6-8h ; 热风循环(cycling warm air): 100-120°C, 6-8h ; 真空烘箱(vacuum drying oven): 100-120°C, 4-6h
加工温度 processing temperature	入料段(feed section): 215-225°C; 熔融段(compressing section): 220-250°C; 射嘴段(metering section): 200-240°C
背压 back pressure	5-10Mpa
注射压力 injection pressure	70-130Mpa
保压压力 packing pressure	40-90Mpa
模具温度 mold temperature	70-100°C
后处理 post treatment	NA
其它 others	NA

以上数据仅供参考

All the information provided by EPONE only for reference

追求卓越，志存高远

Pursuing excellence, targeting perfection

For more information, please refer to <http://www.epone.com.cn>

产品性能参数

product performance parameters

性能 (properties)	测试标准 (test standard)	单位 (unit)	数据 (test result)
物理性能 (physical properties)			
密度 density	ISO 1183	g/cm ³	1.30
熔点 melting temperature	ISO 11357	°C	220
吸湿性 absorption of moisture			
24 hours in 23°C water	ISO 62	%	---
成型收缩率 molding shrinkage			
纵向 normal	ISO 25557/1	%	0.80
横向 parallel	ISO 25557/1	%	0.75
机械性能 (mechanical properties)			
冲击 impact strength			
无缺口冲击强度 non-notched	ISO 179	kJ/M ²	NB
缺口冲击强度 notched	ISO 180	kJ/M ²	8
拉伸 tensile			
断裂强度 tensile strength	ISO 527-2	MPa	60
断裂伸长率 elongation at break	ISO 527-2	%	50
弯曲 flexural			
断裂强度 flexural strength	ISO 178	MPa	90
弯曲弹性模量 flexural modulus	ISO 178	MPa	2850
硬度 hardness			
洛氏硬度 rockwell hardness	ISO 2039-2	R	115
电气性能 (electrical properties)			
体积电阻率 volume resistivity	IEC 60093	Ω.cm	10 ¹⁵
表面电阻率 surface resistivity	IEC 60093	Ω	10 ¹⁴
介电强度 dielectric strength	IEC 60243	kV/mm	34
燃烧性能 (flammability properties)			
阻燃 flame retardant	UL 94	—	V0
氧指数 oxygen index	ISO4589	%	---

除特别说明外，以上数据均指在环境相对湿度 (RH) = 0 及 23°C 条件下测得。

以上数据为典型值，仅供参考，不作质量保证之承诺。

All the data above was measured at 23°C and RH=0 unless otherwise stated, all is typical data, only for reference, not the permit of quality assurance.

追求卓越，志存高远

Pursuing excellence, targeting perfection

For more information, please refer to <http://www.epone.com.cn>